

Devon

BASIC INFORMATION

Launch Date	01/2017	Tariff item number	5407520000
Delivery time weeks special lab dip	2	Number of colour ways	36
Country of origin	China	Characteristics	Texture
Vertical repeat cm	Plain	Vertical repeat inch	Plain
Horizontal repeat cm	Plain	Horizontal repeat inch	Plain
Full roll diameter in cm	32	Full roll diameter in inch	12.6
Face in	Yes	Minimum for special colour m	1000
Average piece length m	50	MID	CNTONFOR12

CATEGORY

Colouring type	Piece dyed	Type of print or dye - vat	Yes
Type of finish - thermofixed	Yes	After treatment - brushed or emerised	Yes

Care codes



Use codes

Upholstery	Yes	Bed covering	Yes
Accessories	Yes		

FABRIC TYPE

Composition	100% Polyester	Average yarn number	20.73
Weaving type - dobby	Yes	Construction	46x28
Useable width cm	143.00	Useable width inch	56.3
Full width cm	145	Full width inch	57.1
Woven	Yes	Weight gm ²	357
Thickness mm	0.000		

ENVIRONMENTAL STANDARDS



FR STANDARDS

BS5852 source 0	Yes	CAL 117 Complies	Yes
FMVSS 302 Pass	Yes	NFPA 260	Yes

SPECIFICATIONS

Devon

Martindale rubs	80,000	Colour fastness to light	4
Pilling	4	Brush pilling	4-5
Wyzenbeek double rubs	105,000	Wyzenbeek wire screen double rubs - residential use, stopped after 15 000 double rubs	15,000
Wyzenbeek cotton duck type heavy upholstery	Yes	Wyzenbeek wire screen heavy duty	Yes
Colour fastness to light - ISO 105-B02			
Colour fastness to light	4		
Colour fastness to water - ISO 105-E01			
Colour fastness to water	4-5		
Colour fastness to dry rub - ISO 105-X12			
Colour fastness dry rub	4-5		
Colour fastness to wet rub - ISO 105-X12			
Colour fastness wet rub	4		
Colour fastness to wear - ISO 12947-2			
Colour fastness to wear	4		
Tearing strength - ISO 13937-3			
Tearing strength warp N	73	Tearing strength weft N	74
Tensile strength - ISO 13934-1			
Tensile strength warp N5cm	1300	Tensile strength weft N5cm	590
Elongation - ISO 13934-1			
Elongation warp %	33.5	Elongation weft %	22.5
Seam slippage - ISO 13936-2			
Seam slippage warp mm	3	Seam slippage weft mm	2
Resistance to domestic washing 30°C (indicated in %) - ISO 6330			
Dimensional change warp after ironing	-0.33	Dimensional change warp	-0.40
Dimensional change weft after ironing	-0.40	Colour fastness ISO 105 C06	4-5
Dimensional change weft	-0.60		
Resistance to domestic washing 60°C (indicated in %) - ISO 6330			
Dimensional change warp	-1.39	Dimensional change warp after ironing	-1.13
Dimensional change weft	-1.89	Dimensional change weft after ironing	-1.60

Devon

Colour fastness ISO 105 C06 4-5

Resistance to dry cleaning P (indicated in %) - ISO 105 D01

Dimensional change warp	-0.86	Dimensional change warp after ironing	-0.66
Dimensional change weft	-1.20	Dimensional change weft after ironing	-1.06
Colour fastness ISO 105 D01	4-5		

Dimensional stability (indicated in %) - ISO 3759

Dimensional change warp	-0.05	Dimensional change warp after ironing without steam	0.13
Dimensional change warp after ironing with steam	0.13	Dimensional change weft	-0.15
Dimensional change weft after ironing without steam	0.13	Dimensional change weft after ironing with steam	0.40

CONSTRUCTION

Yarn 1

Weft Composition	100% Polyester	Weft Is Filament	Yes
Weft Is Not High Tenacity	Yes	Weft Is Textured	Yes
Weft Sizes	300D	Weft Textured	Yes
Weft Threads per cm	28	Weft TPM	NA

Yarn 2

Warp Composition	100% Polyester	Warp Is Filament	Yes
Warp Is Not High Tenacity	Yes	Warp Is Textured	Yes
Warp Sizes	150D	Warp Textured	Yes
Warp Threads per cm	46	Warp TPM	NA